

Polymer Systems Technology Limited

UK & Ireland Distributor



© 2010 - Polymer Systems Technology Limited TM
Unit 2. Network 4. Cressex Business Park,
Lincoln Road, High Wycombe, Bucks. HP12 3RF
Phone +44 (0) 1494 446610
Fax: +44 (0) 1494 528611
Web: <http://www.siliconepolymers.co.uk>
Email: sales@silicone-polymers.co.uk





LS-8941

NuSil Technology LLC
 1050 Cindy Lane • Carpinteria, CA 93013
 805/684-8780 • 805/566-9905 Fax
 www.nusil.com • silicone@nusil.com

An ISO 9001 and AS9100
 Certified Company

Optically Clear, High Durometer Silicone Elastomer

Description

- Two-part, optically clear, non-phenyl containing addition cure silicone
- Designed to stay thermo-optically stable with heat and UV exposure
- 24 hours minimum work time
- 80 Type A durometer aids with scratch resistance and reduces tackiness

Applications

- For molding or casting hard, non-yellowing lenses for LED, solar or other applications where a hard, optically-stable silicone is needed
- Viscosity is designed to be used with conventional Liquid Injection Molding equipment, and the material is self-leveling for casting application techniques

Properties	Average Result	ASTM	NT-TM
Uncured:			
Appearance	Transparent Liquid	D2090	002
Viscosity, Part A	27,500 cP (27,500 mPas)	D1084, D2196	001
Viscosity, Part B	25,000 cP (25,000 mPas)	D1084, D2196	001
Viscosity, tested within 30 minutes after catalyzation	21,500 cP (21,500 mPas)	D1084, D2196	001
Refractive Index	1.41	D1218, D1747	018
UV/Visible Spectrophotometry @ 400 nm, 1 cm path length	94 %T	E275	100
Cured: 30 minutes @ 150°C (302°F)			
Specific Gravity	1.07	D792	003
Durometer, Type A	80	D2240	006
Tensile Strength	1,250 psi (8.6 MPa)	D412	007
Elongation	65%	D412	007
Tear Strength	55 ppi (9.7 kN/m)	D624	009
UV/Visible Spectrophotometry @ 400 nm, 1.9 mm path length	95 %T	E275	100

Properties tested on a lot-to-lot basis. Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

Instructions for Use

Mixing

Use with mix and dispense equipment in a 1:1 mix ratio. If mixing by hand, take care to minimize air entrapment.

Vacuum Deaeration

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply vacuum, up to 28 inches Hg, to a container rated for use and of volume at least four times that of material being deaerated. Hold vacuum until presence of air is no longer evident.

Substrate Considerations

Cures in contact with most materials. Exceptions include sulfur cured organic rubbers, latex, chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents.

Note: Some bonding applications may require the use of a primer. NuSil Technology's LS3-3200 silicone primer is recommended.

Packaging

- 50 Gram Kit
- 50 mL SxS Kit
- 2 Pint Kit (910 g)
- 2 Gallon Kit (7.28 kg)
- 10 Gallon Kit (36.4 kg)

Warranty

6 Months

RoHS and REACH Compliance

LS-8941 is compliant with the Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment (RoHS) regulation contained in Article 4(1) of the European Parliament and Council's Directive 2002/95/EC. RoHS mandates that manufacturers restrict the use of lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls, polychlorinated biphenyls, and polybrominated diphenyl ethers in electrical and electronic equipment.

LS-8941 is also compliant with the Registration, Evaluation, and Authorization of Chemicals (REACH) regulation (European Union 1907/2006). LS-8941 does not contain any of the 16 chemicals identified as Substances of Very High Concern (SVHC) by the European Chemicals Agency (ECHA), which oversees REACH compliance.

Please contact NuSil Technology's Regulatory Compliance department with any questions or for further assistance.

Specifications

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

Warranty Information

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 6 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

Warnings About Product Safety

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

Patent / Intellectual Property Warning

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.